Machine Finished Kraft Paper (50–90 g/m²)

Origin: Poland

PAPERMAT REF.
PM-KR-050/090

MAIN FEATURES

- very good parameters in finished product like considerable strength, high smoothness and excellent formation
- great printability and perfect runnability for different applications in complex packaging converting processes
- perfect platform designed for various coating & varnish applications

CERTIFICATES

- PEFC
- FSC®
- Environmental manag. ISO 14001
- Quality management ISO 9001
- Food safety management ISO 22000
- Energy management ISO 50001
- Health & Safety ISO 45001
- 100% ECF fibres

IN COMPLIANCE WITH

- BfR XXXVI
- FDA §§ 176.170
- FDA §§ 176.180
- Regulation (EC) no 1907/2006 (REACH)
- Regulation (EC) no 1935/2004
- Directive 94/62/EC
- EN 71-3
- D.M. 21/3/73

PROPERTY	TEST STANDARD	UNIT	TYPICAL VALUE — BASIS WEIGHT (g/m²)					
			50	60	70	75	80	90
Basis weight	ISO 536	g/m²	50	60	70	75	80	90
Moisture content	ISO 287	%	6,0	6,0	6,0	6,0	6,0	6,0
Tensile strength MD	ISO 1924-3	kN/m	5,0	6,2	6,9	7,1	7,2	7,4
Tensile strength CD	ISO 1924-3	kN/m	2,3	2,9	3,2	3,3	3,4	3,5
Opacity	ISO 2471	%	71	73	77	79	81	85
Air resistance	ISO 5636-5	s	≥25	≥30	≥30	≥30	≥25	≥20
Burst strength	ISO 2758	kPa	200	220	260	260	300	300
Water absortiveness COBB'60	ISO 535	g/m²	25	25	25	25	25	25
Brightness ISO C/2°	ISO 2470-1	%	88	88	88	88	88	88
Bendtsen roughness	ISO 8791-2	ml/min	230	230	230	230	230	230

All figures mentioned above may be subject to technical changes.
For more detailed information, please refer to the safety declaration.