Napkin Tissue (21 g/m²)

Origin: China · Napkin 21.0gsm-1ply

PAPERMAT REF.
PM-TS-021

PROPERTY	TEST METHOD	UNIT	RANGE
PHYSICAL PROPERTIES			
Basis Weight	GB/T 451.2-2002	g/m² (1 ply)	21 ± 1.5
Ply	Observe area	ply	1
Thickness	TA 89-100	µm (1 ply)	≥ 60 (lower control limit)
MD Tensile Strength	GB/T 12914-2008	gf/25mm (1 ply)	720 ± 145
CD Tensile Strength	GB/T 12914-2008	gf/25mm (1 ply)	450 ± 100
MD Wet Tensile	GB/T 12914-2008	gf/25mm (1 ply)	≥ 120 (lower control limit)
Softness	GB/T 8942-2002	mN (1 sheet)	≤ 100 (upper control limit)
Brightness	GB/T 7974-2002	% ISO (60 ply)	80.0 – 90.0
APPEARANCE			
Pin Hole — Total	GB/T 20808	pcs/m²	≤ 20
Pin Hole — 2 ≤ φ ≤ 5 mm	GB/T 20808	pcs/m²	≤ 20
Pin Hole — 5 ≤ φ ≤ 8 mm	GB/T 20808	pcs/m²	≤ 1
Pin Hole — 8 ≤ φ ≤ 12 mm **(MD: 30 m · CD: full width, observe area)**	GB/T 20808	pcs/m²	≤ 2
Dirt — Total	GB/T 1541	pcs/m²	≤ 50
Dirt — 0.2–1.0 mm²	GB/T 1541	pcs/m²	≤ 50
Dirt — 1.0–2.0 mm²	GB/T 1541	pcs/m²	≤ 4
Dirt — 2.0–5.0 mm² **(MD: 60 m · CD: 2.5 m, observe area)**	GB/T 1541	pcs/m²	≤ 2